

SunTek
WINDOW FILMS

Carbon

AUTOMOTIVE
WINDOW FILMS



The Skin Cancer Foundation recommends this product as an effective UV protectant.

	%VLT	%TSER	%VLR	%GR	%UV
Carbon 85	81	28	9	8	99
Carbon 70	67	27	8	24	99
Carbon 55	55	31	7	38	99
Carbon 45	44	34	7	50	99
Carbon 38	38	37	6	57	99
Carbon 35	36	38	6	59	99
Carbon 25	25	40	6	72	99
Carbon 18	18	44	5	80	99
Carbon 5	5	46	5	94	99

VLT - Visible Light Transmission TSER - Total Solar Energy Rejection GR - Glare Reduction
 VLR - Visible Light Reflectance UV - Ultraviolet Protection

The solar performance data reported for SunTek® automotive window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement as measured on single pane, 1/4 inch (6mm), clear glass. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.

- Innovative carbon technology
- Non-reflective, attractive appearance with protection against change in color.
- Good heat rejection, glare reduction and UV protection
- No signal interference
- Manufacturer's lifetime limited warranty* with protection against change in color

suntekfilms.com